

LIGNOCEL

Natural wood fibers with natural, pure minerals

Basic raw material

Selected softwood

Chemical and physical properties

Colour		light brown
Structure		granules
Average particle size / particle range		4 mm - 6 mm
Loss on drying	max.	14 %
Oxide ash (450 °C, 4 h)	~	10 %
pH-value (10 % suspension)		5.5 - 7.5
Bulk density (in accordance with DIN EN ISO 60)		350 g/l - 500 g/l

General remarks

LIGNOCEL Combi Plus is a natural, low dust animal bedding used for farm animals.

As with all natural products slight differences to the above given values may arise.

Release date: 2015-10 / 1 page



J. RETTENMAIER & SÖHNE GMBH + CO KG
Fibers designed by Nature
Holzmühle 1
D-73494 Rosenberg

Telephone: +49 7967 152-0
Telefax: +49 7967 152-222